

UTILITY PATENT APPLICATION TRANSMITTAL LETTER

(Only for new nonprovisional applications under 37 CFR 1.53(b)

Docket No. P15484US00

To the Commissioner of Patents:

Transmitted herewith for filing is a **continuation** patent application of PCT/SE99/00627 filed April 20, 1999, of Kersti STRANDQVIST,

corresponding to Swedish application 9801490-5, filed April 28, 1998, entitled: ABSORBENT STRUCTURE HAVING IMPROVED ABSORPTION PROPERTIES

Enclosed are:

Х	10 pages of specification.		
Х	4 sheets of formal drawings.		
Х	a newly-executed declaration of the inventor.		
	a copy of an executed declaration of the inventor from prior application Serial No. , filed .		
	incorporation by reference. The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied as indicated in the preceding box, is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein.		
Х	an assignment of the invention to SCA HYGIENE PRODUCTS AB, including assignment cover sheet.		
	Information Disclosure Statement with Form PTO-1449.		
	copies of the Information Disclosure Statement citations.		
Х	preliminary amendment.		
Х	return receipt postcard (MPEP 503), specifically itemized.		
	applicant claim small entity status.		
	a certified copy of the Priority Document.		
Х	other: application data sheet. PETITION TO REVIVE		

If a CONTINUING APPLICATION, check appropriate box and supply the requisite information.

[X] Continuation [] Divisional [] Continuation-in-part (CIP)

of prior application No. PCT/SE99/00627, filed April 20, 1999.

Х	Customer No. 000466.
Х	Correspondence address is: YOUNG & THOMPSON, 745 South 23rd Street, Second Floor, Arlington, Virginia 22202.
x	Telephone: (703) 521-2297. Telefax: (703) 685-0573 or (703) 979-4709.

UTILITY PATENT APP	Continued	AL LETTER	Docket No. P15484US0	
	CLAIMS AS	FILED		
	NO. FILED	NO. EXTRA	RATE	FEE
BASIC FEE			\$ 710	\$ 710
TOTAL CLAIMS	12 - 20 =	0	x\$ 18	0
INDEPENDENT CLAIMS	1 - 3 =	0	x\$ 80	0
MULTIPLE DEPENDENT CLAI	M		\$ 270	
			TOTAL	\$ 710
If applicant h CFR 1.9 and and enter ar	nas small entity status under 37 1.27, then divide total fee by 2, nount here.	SMALL I		\$

	_	
X	A cr	neck in the amount of \$750 to cover the filing fee is enclosed.
X	bavr	Commissioner is hereby authorized to charge indicated fees and credit any over- nents to Deposit Account No. 25-0120 in the name of Young & Thompson, as cribed below. A duplicate copy of this sheet is enclosed.
		Charge the amount of \$ as filing fee.
	Х	Credit any overpayment.
	Х	Charge any additional fee required under 37 CFR 1.16 and 1.17, during the pendency of this application.
		Charge the issue fee set in 37 CFR 1.18 at the mailing of the Notice of Allowance.

Benoit Castel Registration No. 35,041 745 South 23rd Street Arlington, VA 22202 Telephone 703/521-2297

Benoît Castel

October 30, 2000

INVENTOR INFORMATION

Inventor One Given Name:: KERSTI

Postal Address Line One:: HEYMANS VAG 10 City:: STRANDQVIST

City:: SWEDEN Country:: PIXBO SWEDEN 435 43 City of Residence:: Country of Residence::
Postal or Zip Code:: SWEDEN

CORRESPONDENCE INFORMATION

Citizenship Country::

Correspondence Customer Number:: 000466

YOUNG & THOMPSON Name Line One::

Address Line One::

745 SOUTH 23RD STREET SECOND FLOOR ARLINGTON Address Line Two:: City:: VIRGINIA State or Province::

U.S.A. Country:: 22202 Postal or Zip Code::

703-521-2297 Telephone:: 703-685-0573 Fax One:: 703-979-4709 Fax Two::

APPLICATION INFORMATION

F ł.

\$ Į.

lj.

ABSORBENT STRUCTURE HAVING IMPROVED Title Line One::

P15484US00

ABSORPTION PROPERTIES Title Line Two::

Total Drawing Sheets:: 4 Total Drawing S.:: YES
Formal Drawings?:: UTILITY

REPRESENTATIVE INFORMATION

Representative Customer Number:: 000466

CONTINUITY INFORMATION

Docket Number::

CONTINUATION OF This application is a:: PCT/SE99/00627 >Application One:: APRIL 20, 1999 Filing Date::

PRIOR FOREIGN APPLICATION

9801490-5 Foreign Application One::

APRIL 28, 1998 Filing Date::

SWEDEN Country:: Priority Claimed:: YES

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of

Kersti STRANDQVIST

Serial No. (unknown)

Filed herewith

ABSORBENT STRUCTURE HAVING IMPROVED ABSORPTION PROPERTIES

PRELIMINARY AMENDMENT

Commissioner of Patents

Washington, D.C. 20231

Sir:

Prior to the first Official Action, please amend the above-identified application as follows:

IN THE SPECIFICATION:

Page 1, after the title, insert the following paragraph:

--This application is a continuation of international application PCT/SE99/00627 filed April 20, 1999, which claims the priority of Swedish application 9801490-5 filed April 28, 1998.--

IN THE CLAIMS:

Claim 3, line 1, cancel "or 2".

Claim 5, line 1, change "any of the preceding claims" to --claim 1--.

Claim 6, line 1, change "any of the preceding claims" to --claim 1--.

Claim 7, line 1, change "any of the preceding claims" to --claim 1--.

Kersti STRANDQVIST

Claim 8, line 1, change "any of the preceding claims" to --claim 1--.

Claim 9, line 1, change "any of the preceding claims" to --claim 1--.

Claim 10, line 1, change "any of the preceding claims" to --claim 1--.

Claim 11, line 1, change "any of the preceding claims" to --claim 1--.

Claim 12, line 5, change "any of the claims 1-11" to --claim 1--.

Respectfully submitted,

YOUNG & THOMPSON

Benoît Castel Attorney for Applicant Registration No. 35,041 745 South 23rd Street Arlington, VA 22202 Telephone: 703/521-2297

October 30, 2000

15

20

25

1

ABSORBENT STRUCTURE HAVING IMPROVED ABSORPTION PROPERTIES

Technical field

The present invention refers to an absorbent structure in an absorbent article such as a diaper, a pant diaper, an incontinence guard, a sanitary napkin or the like, said structure comprising a combination of a porous material such as fibers and/or foam, and superabsorbent material. The invention also refers to an absorbent article containing such an absorbent structure.

10 Background of the invention

For absorbent articles of the above mentioned kind it is of essential importance that they have the ability to quickly receive and absorb large amounts of liquid. It is further of importance that liquid can be distributed from the wetting area to other parts of the absorbent structure, so that the total absorption capacity of the article can be utilized.

It is further essential that the absorbent structure can retain the liquid also when exerted to external loadings, such as when the user is moving, is sitting or lying down.

One problem, especially for diapers and incontinence guards, which are intended to receive and absorb relatively large amounts of liquids, is that they risk to leak before their total absorption capacity is fully utilized. A reason for such a leakage is that the absorbent structur, especially at repeated wettings, has a decreased capacity to quickly receive and absorb large amounts of liquid.

Absorbent articles of this kind comprise a liquid pervious topsheet, a liquid impervious backsheet and an absorbent structure arranged therebetween, said absorbent structure comprising a liquid acquisition layer located adjacent the liquid pervious topsheet, and one and more liquid storage and liquid distribution layers.

In order to obtain a high absorption capacity and a high liquid retaining capacity when the article is exerted to outer loadings it often contains so called superabsorbents.

Superabsorbents are crosslinked polymers with capacity to absorb liquid in an amount

10

15

20

प्राथम के प्राथम के प्राथम के अपने के प्राथम के अपने के प्राप्त के अपने के प्राप्त के प्राप्त के प्राप्त के प्र

several times, 10 times or more, their own weight. They further have the capacity to retain absorbed liquid also when exerted to an external pressure. They have gained wide use in absorbent articles, at which they usually are in particulate form, such as grains, granules, flakes or fibers and they are mixed or layered with other absorption materials, usually cellulosic fibers.

The efficiency of a superabsorbent is dependent on many factors, such as where and how the superabsorbent is mixed into the absorbent structure, what physical shape the superabsorbent particles have, and the properties of the superabsobent such as absorption rate, gel strength and liquid retaining capacity.

An important reason that the absorbent structure functions unsatisfactory at repeated wettings, i e at the second and third wetting occasions, is that it is difficult for the superabsorbent material to maintain its structure and shape after the superabsorbent particles have swollen. The firmness and shape of the superabsorbent particles can for example be weakened at outer loadings. By the fact that a superabsorbent at external loadings and after the first and second wetting has difficulty to maintain its structure and shape, a common phenomena called gelblocking occurs. Gelblocking means that the superabsorbent when wetted forms a gel which blocks the pores in the porous fiber structure and by that detoriates the liquid transport from the wetting area to other parts of the absorbent structure. This involves that the total absorbion capacity of the absorbent structure is not optimally utilized, and also involves an increased risk for leakage.

The problem of gelblocking increases when the amount of superabsorbent material in an absorbent structure is high. In order to make an article that is discrete and comfortable to wear it is however a desire that the article is thin. In order to maintain a high liquid absorption capacity such thin articles often have a relativley high amount of superabsorbent material.

25

10

15

20

25

In order to improve the capacity of the superabsorbent to maintain its structure even at an outer loading and after a plurality of wettings the superabsorbent material is often crosslinked in two steps. The first crosslinking is a so called internal crosslinking and is made by copolymerization of acrylic acid and at least one bifunctional agent under the formation of a network.

Copolymerizeable crosslinking agents used in superabsorbent polymers usually consist of bifunctional substances such as diacrylate esters and allylmethacrylates of trifunctional substances such as 1,1,1-trimethylol propane triacrylate and triallylamine or of tetra-functional substances such as tetraallyloxyethane.

The second crosslinking is a so called surface crosslinking and involves that the superabsorbent easier maintains its original shape also when exerted to external loads and after several wettings. Surface crosslinking of the superabsorbent is usually made by esterification of carboxylic groups. One example of surface crosslinking agents are polyhydroxy substances. Another example is organic carbonates, preferably ethylene carbonate in acqeous solution. A third example is the use of diglycidyl compounds, especially ethylene glycol-diglycidylether (EDGE).

It is also known through e g US 4,043,952 to surface crosslink a superabsorbent based on an anionic polyelctrolyte with a polyvalent metal ion, for example aluminum. The surface crosslinking occurs with ionic bonds. It is stated that the superabsorbent in question has an improved dispersability in an acqeous medium. There is no mentioning about an effect on the absorption capacity in an absorbent article.

Through EP-B-0 248 963 it is known to surface crosslink a superabsorbent of anionic character with a polyquartenary amine for increasing the absorption capacity of the superabsorbent. Also here the crosslinking is made by means of ionic bonding.

The object and most important features of the invention

The object of the present invention is to provide an absorbent structure in an absorbent article of the above mentioned kind and which contains a high amount of superabsor-

And Andrew State Come and Andrew State of the State State

5

10

15

20

25

30

bent material, said absorbent structure having improved properties with respect to liquid acquisition capacity and distribution capacity at repeated wettings. This has according to the invention been achieved by the fact that the absorbent structure contains at least 50 % by weight superabsorbent material, based on the total weight of the structure in dry condition in at least one area thereof in which the superabsorbent material is distributed, said superabsorbent material is crosslinked by means of ionic bonds.

The superabsorbent material can also be covalently crosslinked by means of another crosslinking agent.

The superabsorbent material preferably comprises a polymer with anionic functional groups, for example a crosslinked polymer of a polyacrylate having functional carboxy groups.

The superabsorbent material is preferably crosslinked by cations, which by means of ionic bonds are bonded to the anionic functional groups of the superabsorbent material. According to one embodiment the cationic crosslinking agent comprises a polyvalent metal ion, for example aluminum, zirconium, chrome, titanium or zinc. According to a preferred embodiment the ionic crosslinking is made by aluminate ions, Al(OH)⁴.

The superabsorbent material can either be surface crosslinked by the ionic crosslinker or substantially homogeneously crosslinked therewith.

According to one embodiment the absorbent structure contains at least 70 % by weight superabsorbent material, based on the total weight of the structure in dry condition in at least one area in which the superabsorbent material is distributed.

The invention further refers to an absorbent article such as a diaper, a pant diaper, an incontinence guard, a sanitary napkin or the like comprising a liquid pervious topsheet, a liquid impervious backsheet and an absorbent structure arranged therebetween, at which the absorbent structure is of the kind stated above.

10

15

20

25

30

Description of drawings

The invention will in the following be closer described with reference to the accompanying drawings.

Fig. 1a and b show in the form of diagrams a comparison of the utilization degree of the absorption capacity of an absorbent article on different distances from the wetting area and where the article contains different superabsorbents in an amount of 50 and 70 % by weight respectively.

Fig. 2 a and b show in the form of bar charts the acquisition time at the first, second and third wetting occasions in absorbent articles containing different superabsorbents in an amount of 50 and 70 % by weight respectively.

Fig. 3 a and b shows in the form of diagrams the rewet after the first, second and third wetting occasions of absorbent articles containing different superabsorbents in an amount of 50 and 70 % by weight respectively.

Fig. 4 a and b show in the form of bar charts the momentaneous acquisition time under a certain load at the first, second, third and fourth wetting occasions in absorbent articles containing different superabsorbents with a content of 50 and 70 % by weight respectively.

Description of embodiments

Superabsorbent materials are defined as such materials that under gel formation can absorb many times their own weight, 10 times or more, of body liquids and test liquids comparable thereto such as synthetic urine or 0.9 % saline solution. Such materials may e g be hydrogel-forming polymers in the form of alkali salts of polyacrylic acid, polymethacrylic acid, copolymers of acrylic- and methacrylic acid with other monomers, acrylic acid grafted starch, polysaccharides such as carboxymethyl starch, carboxymethyl cellulose, xanthane, alginate, chitosane, pectine, guar gum, and peptides and proteins etc. The hydrogel forming polymers are usually crosslinked for making them water insoluble. Commonly used crosslinkers are ethylene glycol dimethacrylate, diethylene glycol diacrylate, allylmethacrylate, 1,1,1-trimethylolpropane triacrylate, triallyamine and tetraallyl oxyethane, which are bonded to the polymeric structure by means of covalent bonds.

10

15

20

25

30

According to the invention the superabsorbent is surface crosslinked or homogeneously crosslinked by a polyvalent crosslinking agent by means of ionic bonds. Besides it is preferably also covalently crosslinked by another crosslinking agent. The superabsorbent material preferably comprises a polymer with anionic functional groups such as carboxy groups, sulphonate groups, sulphate groups, phosphate groups, amide groups or nitrile groups, preferably however carboxy groups. The ionic crosslinking agent consists of cation, which by ionic bonds are bonded to the anionic functional groups of the superabsorbent material. The cation preferably comprises a polyvalent metal ion such as aluminum, zirconium, chrome, titanium or zinc.

Preferably the crosslinking agent is an aluminate ion, Al(OH)⁴⁻ in accordance with what is disclosed in the German patent application no. 198-18852.8 filed the same day. When producing such a superabsorbent aluminate ions are added to a water-containing gel of a carboxy group containing polymer, e g a polyacrylate, which preferably is crosslinked by means of covalent bonds in a conventional way. The gel is crosslinked with the aluminate ions before drying to a powder or granules, at which a homogeneously ionically crosslinked hydrogel structure is obtained.

When a superabsorbent absorbs liquid and swells the covalent bonds to the cross-linking agent are successively broken up, which leads to that the superabsorbent looses its gel stability in connection with the swelling. A superabsorbent however which is surface crosslinked or homogeneously crosslinked by a ionic crosslinking agent maintains its gel stability afte swelling in a better way, due to that the ionic bonds can be rearranged and recreated as the polymer swells, which a covalent bond is not able to do.

The superabsorbent according to the present invention can thus be both covalently and ionically crosslinked, or only ionically crosslinked. The ionic crosslinking can either be on the surface of the superabsorbent particles or homogeneously through the entire structure of the superabsorbent.

The porous structure in which the superabsorbent is contained can be of optional kind, such as a fibrous structure of cellulosic fluff pulp, synthetic fibers of different kind, regenererated cellulosic fibers or mixtures thereof. The porous structure can also consist of an absorbent foam material.

5

The superabsorbent can either be mixed with the porous structure or be applied as a layer therein. Is is also possible to apply a layer of superabsorbent material between two layers of porous material.

10

The amount of superabsorbent material in the absorbent structure should be at least 50 % by weight calculated on the weight of the structure in dry condition in at least one area in which the superabsorbent material is distributed. This means that in for example a double- or multilayered structure with different amounts of superabsorbent material in the different layers, the amount of superabsorbent material should be at least 50 % by weight in at least one of the layers. The total amount of superabsorbent material in the entire absorbent structure, however, could be lower than 50 % by weight.

15

According to one embodiment the amount of superabsorbent material in the absorbent structure should be at least 70 % by weight calculated on the weight of the structure in dry condition in at least one area in which the superabsorbent material is distributed

20

The physical shape of the superabsorbent material is important for its function in the absorbent structure and is preferably in the form of a powder, grains or granules.

25

Below a number of tests are disclosed which were made with respect to utilization degree, acquisition time and rewet in absorbent structures containing a combination of pulp fibers (chemical pulp) and 50 and 70 % by weight respectively of a superabsorbent material of four different types. The test absorbent bodies were of the size 28x10 cm, with a surface weight of 300 g/m² and a bulk of 3 cm³/g. The superabsorbent particles were substantially homogeneously mixed with the pulp fibers.

30

10

15

The superabsorbents that were used were a commersially available superabsorbent from Clariant GmbH named Sanwet IM 7100 and three different test substances of a polyacrylate homogeneously crosslinked by aluminate ions according to above and which besides was covalently crosslinked. The test substances were named E271/97, E214/97 and E222/97 and were supplied by Clariant GmbH and Clariant Corp.

Utilization degree

The absorbent bodies were placed with an inclination of 30° in order to imitate the placing of the diaper during use. The lower end was in contact with a liquid bath of synthetic urine (formula according to below) and was allowed to suck liquid during 60 minutes. The length of the wet area was measured. Test bodies were cut in smaller pieces corresponding to different lengths and were weighed. The utilization degree was calculated according to the formula:

Utilization degree = Absorbed weight of urine (g) / Theoretical absorption capacity (g), at which

Absorbed weight of urine = Weight of the sample after absorption - Dry weight;

Theoretical absorption capacity = Weight of superabsorbent (g) in sample · Free swell
capacity in synthetic urine + Weight pulp fibers (g) · Absorption capacity of pulp.

The absorption capacity for pulp fibers were measured after 60 minutes of free absorption in synthetic urine to be 8 g urine / g pulp.

Free swell capacity for the superabsorbent was measured by the below described method.

The result is shown in the diagrams in Fig. 1 a and b, from which it can be seen that the utilization degree at the portions located furthest away from the wetting area were clearly better for the test substances as compared to the reference.

25

10

15

20

25

30

Formula for synthetic urine

0.66 g/l magnesium sulphate, 4.47 g/l potassium chloride, 7.60 g/l sodium chloride, 18.00 g/l urea, 3.54 g/l potassium dihydrogen phosphate, 0.745 g/l sodium hydrogen phosphate, 1.00 g/l 0.1-%-ig triton, 0.4 g/l Nykockin (colour), rest de-ionized water.

Free swell capacity

Pouches of polyester net 7x12 cm were prepared. 0.2 g of superabsorbent were weightd and placed in the pouches, which were welded and weighed. The pouches were immersed in synthetic urine during 60 minutes after which they were taken up, were allowed to drain and were weighed. The difference in weight after and before absorption gives the free swell capacity.

Acquisition time

Three additions of each 80 ml synthetic urine were made through a plexiglass tube (inner diameter 23 mm) placed on the test bodies. The time interval between the additions were 10 minutes. The time it took until all liquid was absorbed was measured (visual observation). The result of the measurements is shown in Fig. 2 a and b. It is seen that the acquisition time at the second and especially the third addition was lower for the absorbent bodies containing the test substances as compared to the reference substance.

Rewet

Rewet was measured after 10 minutes after each addition by placing a filter paper on the wetting area and load it with a weight of 2550 g during 15 seconds. The filter paper was weighed before and after the loading and the rewet was calculated.

The result is shown in Fig. 3 a and b, at which it can be seen that the rewet after the first wetting occasion was substantially the same and very low both for the absorbent bodies containing test substances and the reference substance respectively. For the absorbent bodies containing 50 % superabsorbent (Fig. 1a) there was already after the second

10

15

20

The first regard from Arris regard 18. The first Arrive 18. No. 10. Arrive 18. Arrive 18

addition observed a difference in rewet between the reference body and the test bodies, a difference that reamined also after the third addition. For the absorbent bodies containing 70% superabsorbent (Fig. 3b) the rewet was the same also after the second addition, but after the third addition the difference between the test bodies and the reference body was significant, in such a way that the test bodies had a considerably lower rewet than the reference body.

Momentaneous acquisition time under a certain pressure

The tested absorbent bodies were clamped under a plexiglass disc, which had a circular opening. Four addition each of 80 ml synthetic urine were made through the circular opening via a funnel and a petri disc. The time interval between the additions were 10 minutes. The time it took until all liquid had been absorbed was measured (visual observation). The result is shown in Fig. 4 a and b. The acquisition time for the test substance (E-222/97) was lower at all additions as compared to the reference substance (IM 7100). The difference was biggest at the third and fourth addition. Similar results were obtained with respect to 50 as well as to 70 % by weight superabsorbent.

Besides the shown advantages with respect to improved absorption properties of absorbent structures containing ionically crosslinked superabsorbents the latter have a further important advantage, viz. that they have a higher resistance to mechanical stress that may occur when handling the superabsorbent particles in for example a diaper machine. A superabsorbent particle which is only covalently surface crosslinked and where the surface layer is damaged due to mechanical stress will loose much of its gel stability. A superabsorbent particle which is ionically crosslinked, either homogeneously or only on the surface, will substantially maintain its gel stability even after mechanical damages of parts of the surface layer. In a superabsorbent particle that is ionically surface crosslinked the ionic crosslinking bonds can be redistributed over the particle surface and in such a way repair possible damages in the surface layer.

25

Claims

1. An absorbent structure in an absorbent article such as a diaper, a pant diaper, an incontinence guard, a sanitary napkin or the like, said structure comprising a combination of a porous material such as fibers and/or foam, and superabsorbent material,

characterized in,

that the absorbent structure contains at least 50 % by weight superabsorbent material, based on the total weight of the structure in dry condition in at least one area thereof in which the superabsorbent material is distributed, said superabsorbent material is cross-linked by means of ionic bonds and is in the form of a powder, grains or granules.

2. An absorbent structure as claimed in claim 1,

characterized in,

that the superabsorbent material also is covalently crosslinked.

3. An absorbent structure as claimed in claim 1 or 2,

characterized in,

that the superabsorbent material comprises a polymer with anionic functional groups.

4. An absorbent structure as claimed in claim 3,

characterized in,

that the superabsorbent material is a crosslinked polymer of a polyacrylate having functional carboxy groups.

25

20

5

10

15

5. An absorbent structure as claimed in any of the preceding claims,

characterized in.

that the superabsorbent material is crosslinked by cations which by means of ionic bonds are bonded to the anionic functional groups of the superabsorbent material.

30

6. An absorbent structure as claimed in any of the preceding claims, characterized in,

ţ

10

15

25

that the cationic crosslinking agent comprises a polyvalent metal ion.

- 7. An absorbent structure as claimed in any of the preceding claims, characterized in,
- 5 that the metal ion is aluminum, zirconium, chrome, titanium or zinc.
 - 8. An absorbent structure as claimed in any of the preceding claims, characterized in, that the crosslinking agent is an aluminate ion, Al(OH)⁴.

9. An absorbent structure as claimed in any of the preceding claims,c h a r a c t e r i z e d i n,that the superabsorbent material is surface crosslinked by the ionic crosslinking agent.

- 10. An absorbent structure as claimed in any of the preceding claims, characterized in, that the superabsorbent material is substantially homogeneously crosslinked with the ionic crosslinking agent.
- 20 11. An absorbent structure as claimed in any of the preceding claims, characterized in, that the absorbent structure contains at least 70 % by weight of superabsorbent material, calculated on the total weight of the structure in dry condition in at least one area thereof in which the superabsorbent material is distributed.
 - 12. An absorbent article such as a diaper, a pant diaper, an incontinence guard, a sanitary napkin or the like of the kind comprising a liquid pervious topsheet, a liquid impervious backsheet and an absorbent structure enclosed therebetween, characterized in,
- that the absorbent structure is of the kind stated in any of the claims 1-11.

100

80

60

40

20

0

2.5

5

Utilizaition degree(%)

50 Weight% Superabsorbent




FIG.1a


70 Weight% Superabsorbent Utilization degree $-\times$ E-271/97 – E-214/97 - E-222/97 **→** IM 7100

Total


15.0 17.5 20.0 22.5 28.0 12.5 25.0 10.0 7.5 Distance from wetting point (cm)

FIG.1b


50 Weight% Superabsorbent Acquisition time




70 Weight% Superabsorbent Acquisition time




50 Weight% Superabsorbent Rewet



70 Weight% Superabsorbent Rewet





DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter, which is claimed and for which a patent is sought on the invention entitled:

"Absorbent structure having improved absorption properties"

the specification of which

1	1	is	attached	hereto.

[] was filed on _____as United States Application Number or PCT International Application Number ____and was amended on _____(if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information, which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 (a)-(d) of any foreign application(s) for patent or inventor's certificate or § 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application for patent or inventor's certificate, or any PCT international application having a filing date before that of the application on which priority is claimed:

Country	Application Number	Date of Filing (day/month/year)	Priority Claimed
Sweden	9801490-5	28.04.1999	YES [X] NO []
			YES[] NO[]

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below:

Application Number:

Filing Date:

Application Number:

Filing Date:

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or § 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT international application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

U.S. Parent Application Serial Number:

Parent Filing Date:

Parent Patent No:

U.S. Parent Application Serial Number:

Parent Filing Date:

Parent Patent No:

PCT Parent Number:

Parent Filing Date:

POWER OF ATTORNEY: I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

YOUNG & THOMPSON

Suite 200

745 South 23rd Street

ARLINGTON, Virginia 22202

USA

Phone: 00 1 703 521 2297 Facsimile: 00 1 703 685 0573 I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

nventor's signature: Kerski Trauf	Date: 14/09/2000
Residence: Heymans väg 10	Citizenship: Swedish
Post Office address: 435 43 PIXBO, Sweden	
Full name of second joint inventor (given name, family name):	
Inventor's signature:	Date:
Residence:	Citizenship:
Post Office address:	
Full name of third joint inventor (given, name, family name): Inventor's signature:	Date:
Residence:	Citizenship:
Post Office address:	
Full name of fourth joint inventor (given, name, family name):	
Inventor's signature:	Date:
Residence:	Citizenship:
Post Office address:	